

## CLAIMS

5 What is claimed is:

1. A process for manufacturing a thermoplastic article which comprises the steps:
  - a) Extrusion, blow molding one or more thermoplastic resins into a pre-form;
  - b) and stretch blow molding, said pre-form into a thermoplastic article.

10

2. A process according to claim 1, wherein blow ratio between thermoplastic resin and pre-form is about 1.5:1 or greater.

15

3. A process according to claim 1, wherein wall thickness of said pre-form is uniformly within about 0.010 inches.

- 20 4. A process according to claim 1, wherein multiple cavities are used in said extrusion, molding process.

5. A process according to claim 1, wherein wall thickness of said pre-form is about  
25 0.06 inches to about 0.20 inches.

6. A process according to claim 1, wherein said pre-form is cooled prior to said stretch blow molding process.

30

7. A process according to claim 1, wherein said thermoplastic resin is one or more resins selected from the group consisting of polypropylene, polyethylene, polyamide, and acrylonitrile.

5

8. A process according to claim 7, wherein said polypropylene is selected from the group consisting of a homopolymer of polypropylene, a copolymer of polypropylene, a clarified polypropylene, and a non-clarified polypropylene.

10

9. A process according to claim 1, wherein said thermoplastic article is clear.

15

10. A process according to claim 1, wherein said thermoplastic article is translucent or opaque.

11. A process according to claim 1, wherein polymer molecules in said thermoplastic article are biaxially aligned.

20

12. A thermoplastic pre-form comprised of one or more thermoplastic resins wherein said thermoplastic pre-form is manufactured by a process comprising the step of extrusion blow molding.

25

13. A thermoplastic pre-form according to claim 12, wherein said thermoplastic resins are one or more resins selected from the group consisting of polypropylene, polyethylene, polyamide, and acrylonitrile.

30

14. A thermoplastic article made by the process of claim 1.

15. A process according to claim 1, wherein blow length ratio is about 2.5:1 to about 3.5:1.

5

16. A process according to claim 1, wherein blow width ratio is about 2:1 to about 3:1.